

TYPAR® BUTYL FLASHING

TYPICAL CHARACTERISTICS

FOR COMMERCIAL AND RESIDENTIAL APPLICATIONS

Characteristic	Test Method	Value
Adhesive		Butyl Rubber Copolymer
Thickness		20 mils
UV Stability		180 Days
Application Temperature		30°F (-1°F) to 180°F (82°C)
90° Peel Adhesion (lb/in)		
Plywood		7.2
OSB		2.8
Facer		6.9
Low Temperature Flexibility	(per ASTM D-3330)	PASS
Nail Sealability	(per ASTM D-1970)	PASS
Tensile Strength	(per ASTM D-5034)	55 lbs/in

ROLL SIZES:	4" x 75'		6" x 75'	
	Rolls/Case: 12	Cases/Pallet: 27	Rolls/Case: 8	Cases/Pallet: 27
	9" x 75'		12" x 75'	
	Rolls/Case: 4	Cases/Pallet: 27	Rolls/Case: 4	Cases/Pallet: 27

The information contained herein is to the best of our knowledge accurate and reliable and is provided for the user's assessment and verification. However, since the circumstances and conditions under which such information and the products discussed can be used may vary and are beyond our control, **we make no warranties, express or implied, other than those warranties described in the TYPAR® weather protection system limited warranty located online at www.typar.com/downloads, subject to the limitations and exclusions described therein.**



Made in the USA of US and global components. © 2017, Berry Global Inc.
 TYPAR® is a registered trademark of Berry Global Inc. or its affiliate.
 Please visit TYPAR.com for installation instructions and warranty information.
 Building Wraps | Flashings | Construction Tape | Fasteners

