

Typar® StormWrap™

FOR COMMERCIAL & RESIDENTIAL APPLICATIONS TYPICAL CHARACTERISTICS

Basis Weight	(ASTM D-5261)	7.6 osy
Thickness	(ASTM D-1777)	21.3 mils
Puncture Resistance	(ASTM D-4833-88)	413 lbs
Dry Tensile Strength	(ASTM D-5034)	233 lbs md 191 lbs xd
Pliability	(AC-38)	PASS
Moisture Vapor Transmission Rate	(ASTM E-96-95, procedure A)	9 U.S. perms
“Air-Ins” (Air Leakage Test)	(CCMC Technical Guide MF-07273)	0.003L/(S·M ²) @ 75 pascals
Ultra Violet Light Exposure Resistance (UV)		12 months
Water Resistance Test (Boat Test)	(ASTM D-779)	PASS
Water Ponding Test	(CCMC Technical Guide MF-07193)	PASS
Surface Burning Characteristics	(ASTM-E-84-00a)	
Flame Spread Index		Class A
Smoke Developed Index		PASS

Roll sizes: 5 ft x 75 ft, 10 ft x 75 ft

Miami Dade County Approved NOA. 07-0322.08, ICC Code Approval #ESR-2431

The information contained herein is to the best of our knowledge accurate and reliable and is provided for the user's assessment and verification. However, since the circumstances and conditions under which such information and the products discussed can be used may vary and are beyond our control, we make no warranty, expressed or implied, of merchantability, fitness or otherwise, or of the results to be obtained, or against patent infringement, and we disclaim all liability from any resulting damage or loss.

Typar®, Typar® Weather Protection System, and Typar® StormWrap, are registered trademarks of Fiberweb, Inc.

Fiberweb, Inc., 70 Old Hickory Blvd., Old Hickory, TN 37138 USA, 1-800-284-2780 •
Fax: 615-847-7068, www.typar.com