



TYPAR® METROWRAP For Commercial Applications:

Physical Properties Data Sheet:

PROPERTIES	METHOD	TYPAR® MetroWrap	TYVEK Commercial Wrap
Basis Weight	TAPPI T-410 (oz/yd ²)	3.5	2.7
Breaking Strength	ASTM D-5034 (lbs)	120	83
	ASTM D-5034 (lbs)	120	99 ASTM D882 (lbs/in) 38/35
Air Penetration resistance	TAPPI T-460 (sec/100cc)	> 4800	> 1500
Water Vapor Transmission	ASTM E96-00 Method A (perms)	10	23
Tear Resistance (Trapezoid)	ASTM D-1117 (MD) (lbs)	60	12
	ASTM D-1117 (MD) (lbs)	67	10
Surface Burning Characteristics	ASTM E-84	PASS	PASS
	ASTM E-84	PASS	PASS
Ultraviolet Light (UV) Exposure Resistance	QUV (months)	12	9

The information contained herein is to the best of our knowledge accurate and reliable and is provided for the user's assessment and verification. However, since the circumstances and conditions under which such information and the products discussed can be used may vary and are beyond our control, we make no warranty, expressed or implied, of merchantability, fitness or otherwise, or of the results to be obtained, or against patent infringement, and we disclaim all liability from any resulting damage or loss.

TYPAR®, TYPAR® Weather Protection System, and TYPAR® MetroWrap, are registered trademarks of Polymer Global, Inc.